

# YS2345

## 热固性丙烯酸树脂

### 特性

- 1、电镀件密着性佳
- 2、低温干燥性好
- 3、耐酸碱性优异

### 用途

低温烘烤型电镀五金光油等。

### 性质

| 特性  | 数值          | 单位         |
|-----|-------------|------------|
| 组份  | 丙烯酸共聚物      |            |
| 外观  | 清澈透明        |            |
| 固体份 | 60±2        | %          |
| 黏度  | 10000-20000 | mPa.s/25°C |
| 酸值  | 85-95       | mgKOH/g    |
| 溶剂  | XYL/NBA     |            |
| 色号  | ≤2(Fe-Co)   |            |

### 储存说明

- 远离热及火源, 置于阴凉通风处, 容器保持紧密。
- 本产品自生产日起, 保质期限为 12 个月。

### 包装规格

200kg/桶

### 安全

本产品含溶剂, 必须做好防护措施, 小心操作, 避免接触皮肤与眼睛, 其它详细资料请参考物质安全说明书。

以上资料系经试验所得, 仅供参考, 不作任何保证之用。鉴于树脂功能的局限性及用户要求的多样性, 若使用本公司产品, 使用前请按自身的要求严格试验树脂的适应性及最终产品的稳定性。

版本: 2021-12-03

# YS2345

## Thermosetting Acrylic Resin

### Characteristics

---

- 1、Adhesion on electroplated stuff ;
- 2、Low temperature curing;
- 3、Acid and alkali resistance ;
- 4、Weather resistance;

### Application

---

Applied to low temperature curing electroplated stuff and metal coating varnish.

### Property

---

| Characteristics | Numeric value     | Unit       |
|-----------------|-------------------|------------|
| Component       | Acrylic copolymer |            |
| Appearance      | Clear and bright  |            |
| Solid Content   | 60±2              | %          |
| Viscosity       | 10000-20000       | mPa.s/25°C |
| Acid Value      | 85-95             | mgKOH/g    |
| Solvent         | XYL/NBA           |            |
| Color           | ≤2(Fe-Co)         |            |

### Storability

---

- Keep away from fire source, placed in a cool ventilated place, keep container tightly.
- Shelf time:12 months.

### Packing

---

200Kg/Berrel

### Safety

---

This product contains solvent, Please be careful operation, avoid contacting with skin and eyes, other information please refer to the material safety instruction.

---

The above information is provided for reference only. If you use our products, please strictly verify according to your own requirements .

Version : 2021-12-03