

# YT2328

## 热塑性丙烯酸树脂

### 特性

- 1、无卤 UV 底
- 2、无苯体系
- 3、UV 面层间密着性及 ABS , ABS+PC , PC 等塑材密着性
- 4、耐水性
- 5、润湿性及银粉排列性

### 用途

ABS , PC , ABS+PC 等塑胶底色漆 , UV 及 PU 单组分底漆。

### 性质

特性	数值	单位
组份	丙烯酸共聚物	
外观	清澈透明	
固体份	45±2	%
黏度	10000-20000	mPa.s/25°C
酸值	1-3	mgKOH/g
溶剂	MIBK/BAC/IBA	
色号	≤1(Fe-Co)	
TG	66	°C

### 储存说明

- 远离热及火源, 置于阴凉通风处, 容器保持紧密。
- 本产品自生产日起, 保质期限为 12 个月。

### 包装规格

200kg/桶

### 安全

本产品含溶剂, 必须做好防护措施, 小心操作, 避免接触皮肤与眼睛, 其它详细资料请参考物质安全说明书。

以上资料系经试验所得, 仅供参考, 不作任何保证之用。鉴于树脂功能的局限性及用户要求的多样性, 若使用本公司产品, 使用前请按自身的要求严格试验树脂的适应性及最终产品的稳定性。

版本: 2021-12-03

# YT2328

## Thermoplastic Acrylic Resins

### Characteristics

---

- 1、 Non-halogen UV basecoat ;
- 2、 Non-benzene system;
- 3、 UV interlayer adhesion and adhesion on ABS,ABS+PC,PC ;
- 4、 Water resistance;
- 5、 Wettability and aluminium powder arrangement

### Application

---

Applied to base colored coat on ABS,PC,ABS+PC,one component basecoat for UV and PU.

### Property

---

Characteristics	Numeric value	Unit
Component	Acrylic copolymer	
Appearance	Clear and bright	
Solid Content	45±2	%
Viscosity	10000-20000	mPa.s/25°C
Acid Value	1-3	mgKOH/g
Solvent	MIBK/BAC/IBA	
Color	≤1(Fe-Co)	
TG	66	°C

### Storability

---

- Keep away from fire source, placed in a cool ventilated place, keep container tightly.
- Shelf time:12 months.

### Packing

---

200Kg/Berrel

### Safety

---

This product contains solvent, Please be careful operation, avoid contacting with skin and eyes, other information please refer to the material safety instruction.

---

The above information is provided for reference only. If you use our products, please strictly verify according to your own requirements .

Version : 2021-12-03