

# YT2347

## 热塑性丙烯酸树脂

### 特性

- 1、对塑胶基材的附着力
- 2、作为底漆，对丙烯酸罩光漆、弹性漆、PU 漆和 UV 罩光漆都有附着力
- 3、耐水煮

### 用途

一般用作 UV 底，PU 底，色漆或银漆等。

### 性质

特性	数值	单位
组份	丙烯酸共聚物	
外观	清澈透明	
固体份	40±2	%
黏度	15000-25000	mPa.s/25°C
酸值	< 2	mgKOH/g
溶剂	EAC/BAC/NBA	
色号	≤1(Fe-Co)	
TG	70	°C

### 储存说明

- 远离热及火源，置于阴凉通风处，容器保持紧密。
- 本产品自生产日起，保质期限为 12 个月。

### 包装规格

190kg/桶

### 安全

本产品含溶剂，必须做好防护措施，小心操作，避免接触皮肤与眼睛，其它详细资料请参考物质安全说明书。

以上资料系经试验所得，仅供参考，不作任何保证之用。鉴于树脂功能的局限性及用户要求的多样性，若使用本公司产品，使用前请按自身的要求严格试验树脂的适应性及最终产品的稳定性。

版本：2021-12-03

# YT2347

## Thermoplastic Acrylic Resins

### Characteristics

---

- 1、 Adhesion to plastic substrates ;
- 2、 As a primer, it has strong adhesion to acrylic, elastic, PU and UV finishes;
- 3、 Resistance to boiled ;

### Application

---

Generally used as UV bottom, PU bottom, color paint or silver paint.

### Property

---

Characteristics	Numeric value	Unit
Component	Acrylic copolymer	
Appearance	Clear and bright	
Solid Content	40±2	%
Viscosity	15000-25000	mPa.s/25°C
Acid Value	< 2	mgKOH/g
Solvent	EAC/BAC/NBA	
Color	≤1(Fe-Co)	
TG	70	°C

### Storability

---

- Keep away from fire source, placed in a cool ventilated place, keep container tightly.
- Shelf time:12 months.

### Packing

---

190Kg/Berrel

### Safety

---

This product contains solvent, Please be careful operation, avoid contacting with skin and eyes, other information please refer to the material safety instruction.

---

The above information is provided for reference only. If you use our products, please strictly verify according to your own requirements .

Version : 2021-12-03