

YT2700

热塑性丙烯酸树脂

特性

- 1、层间附着力
- 2、PU 重涂性优
- 3、铝粉定向排布性优

用途

ABS , PC , ABS+PC 等塑胶底色漆 , 橡胶底漆、PU 底漆。

性质

特性	数值	单位
组份	丙烯酸共聚物	
外观	清澈透明	
固体份	50±2	%
黏度	4000-7000	mPa.s/25°C
酸值	2-5	mgKOH/g
溶剂	TOL/BAC	
色号	≤1(Fe-Co)	
TG	50	°C

储存说明

- 远离热及火源, 置于阴凉通风处, 容器保持紧密。
- 本产品自生产日起, 保质期限为 12 个月。

包装规格

200kg/桶

安全

本产品含溶剂, 必须做好防护措施, 小心操作, 避免接触皮肤与眼睛, 其它详细资料请参考物质安全说明书。

以上资料系经试验所得, 仅供参考, 不作任何保证之用。鉴于树脂功能的局限性及用户要求的多样性, 若使用公司产品, 使用前请按自身的要求严格试验树脂的适应性及最终产品的稳定性。

版本: 2021-12-03

YT2700

Thermoplastic Acrylic Resins

Characteristics

- 1、 Interlayer adhesion ;
- 2、 Good PU recoatability;
- 3、 Good aluminium powder arrangement.

Application

Applied to base colored coat on ABS,PC,ABS+PC, basecoat for elastic and PU paint.

Property

Characteristics	Numeric value	Unit
Component	Acrylic copolymer	
Appearance	Clear and bright	
Solid Content	50±2	%
Viscosity	4000-7000	mPa.s/25°C
Acid Value	2-5	mgKOH/g
Solvent	TOL/BAC	
Color	≤1(Fe-Co)	
TG	50	°C

Storability

- Keep away from fire source, placed in a cool ventilated place, keep container tightly.
- Shelf time:12 months.

Packing

200Kg/Berrel

Safety

This product contains solvent, Please be careful operation, avoid contacting with skin and eyes, other information please refer to the material safety instruction.

The above information is provided for reference only. If you use our products, please strictly verify according to your own requirements .

Version : 2021-12-03