

YZ-T200

热塑性丙烯酸树脂

特性

- 1、干性
- 2、UV 面层间密着性晃及 ABS , ABS+PC , PC 等塑材密着性
- 3、耐水性
- 4、润湿性及银粉排列性

用途

ABS , PC , ABS+PC 等塑胶底色漆 , UV 及 PU 单组分底漆 。

性质

特性	数值	单位
组份	丙烯酸共聚物	
外观	清澈透明	
固体份	50±2	%
黏度	20000-40000	mPa.s/25°C
酸值	1-3	mgKOH/g
溶剂	TOL/BAC/IBA	
色号	≤1(Fe-Co)	
TG	70	°C

储存说明

- 远离热及火源, 置于阴凉通风处, 容器保持紧密。
- 本产品自生产日起, 保质期限为 12 个月。

包装规格

200kg/桶

安全

本产品含溶剂, 必须做好防护措施, 小心操作, 避免接触皮肤与眼睛, 其它详细资料请参考物质安全说明书。

以上资料系经试验所得, 仅供参考, 不作任何保证之用。鉴于树脂功能的局限性及用户要求的多样性, 若使用本公司产品, 使用前请按自身的要求严格试验树脂的适应性及最终产品的稳定性。

版本: 2021-12-03

YZ-T200

Thermoplastic Acrylic Resins

Characteristics

- 1、Dryness ;
- 2、UV interlayer adhesion and adhesion on ABS,ABS+PC,PC ;
- 3、Water resistance;
- 4、Wettability and aluminium powder arrangement

Application

Applied to base colored coat on ABS,PC,ABS+PC,one component basecoat for UV and PU.

Property

Characteristics	Numeric value	Unit
Component	Acrylic copolymer	
Appearance	Clear and bright	
Solid Content	50±2	%
Viscosity	20000-40000	mPa.s/25°C
Acid Value	1-3	mgKOH/g
Solvent	TOL/BAC/IBA	
Color	≤1(Fe-Co)	
TG	70	°C

Storability

- Keep away from fire source, placed in a cool ventilated place, keep container tightly.
- Shelf time:12 months.

Packing

200Kg/Berrel

Safety

This product contains solvent, Please be careful operation, avoid contacting with skin and eyes, other information please refer to the material safety instruction.

The above information is provided for reference only. If you use our products, please strictly verify according to your own requirements .

Version : 2021-12-03