

YH2208

羟基丙烯酸树脂

特性

- 1、金属密着性好
- 2、电镀件密着性佳
- 3、耐水性优异

用途

适用于金属及电镀件用 PU 光油或者色漆等。

性质

特性	数值	单位
组份	丙烯酸共聚物	
外观	清澈透明	
固体份	50±2	%
黏度	400-800	mPa.s/25°C
酸值	2-4	mgKOH/g
溶剂	TOL/BAC/XYL	
色号	≤1(Fe-Co)	
羟基含量	1.6 (固体份)	%

储存说明

- 远离热及火源, 置于阴凉通风处, 容器保持紧密。
- 本产品自生产日起, 保质期限为 12 个月。

包装规格

200kg/桶

安全

本产品含溶剂, 必须做好防护措施, 小心操作, 避免接触皮肤与眼睛, 其它详细资料请参考物质安全说明书。

以上资料系经试验所得, 仅供参考, 不作任何保证之用。鉴于树脂功能的局限性及用户要求的多样性, 若使用公司产品, 使用前请按自身的要求严格试验树脂的适应性及最终产品的稳定性。

版本: 2021-12-03

YH2208

Hydroxyl Acrylic Resins

Characteristics

- 1、 Good in Metal adhesion ;
- 2、 Excellent in electroplated part adhesion ;
- 3、 Excellent water resistance.

Application

Applied to PU varnish or paint for metal and electroplated parts.

Property

Characteristics	Numeric value	Unit
Component	Acrylic copolymer	
Appearance	Clear and bright	
Solid Content	50±2	%
Viscosity	400-800	mPa.s/25°C
Acid Value	2-4	mgKOH/g
Solvent	TOL/BAC/XYL	
Color	≤1(Fe-Co)	
OH Content	1.6	%

Storability

- Keep away from fire source, placed in a cool ventilated place, keep container tightly.
- Shelf time:12 months.

Packing

200Kg/Berrel

Safety

This product contains solvent, Please be careful operation, avoid contacting with skin and eyes, other information please refer to the material safety instruction.

The above information is provided for reference only. If you use our products, please strictly verify according to your own requirements .

Version : 2021-12-03